

**NASA
Technical
Memorandum**

NASA TM-103582

**PERFORMANCE OF THERMAL CONTROL TAPE IN THE
PROTECTION OF COMPOSITE MATERIALS TO SPACE
ENVIRONMENTAL EXPOSURE**

By R.R. Kamenetzky and A.F. Whitaker

Materials and Processes Laboratory
Science and Engineering Directorate

April 1992

(NASA-TM-103582) PERFORMANCE OF THERMAL
CONTROL TAPE IN THE PROTECTION OF COMPOSITE
MATERIALS TO SPACE ENVIRONMENTAL EXPOSURE
(NASA) 15 p

CSCL 11C

N92-24982

G3/27 Unclass
0091238



National Aeronautics and
Space Administration

George C. Marshall Space Flight Center

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE April 1992	3. REPORT TYPE AND DATES COVERED Technical Memorandum	
4. TITLE AND SUBTITLE Performance of Thermal Control Tape in the Protection of Composite Materials to Space Environmental Exposure			5. FUNDING NUMBERS	
6. AUTHOR(S) R.R. Kamenetzky and A.F. Whitaker				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) George C. Marshall Space Flight Center Marshall Space Flight Center, Alabama 35812			8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) National Aeronautics and Space Administration Washington, DC 20546			10. SPONSORING/MONITORING AGENCY REPORT NUMBER NASA TM-103582	
11. SUPPLEMENTARY NOTES Prepared by the Materials and Processes Laboratory, Physical Science Division, Science and Engineering Directorate.				
12a. DISTRIBUTION / AVAILABILITY STATEMENT Unclassified — Unlimited			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Thermal control tape flown on the long duration exposure facility (LDEF) experiment AO171 has shown to be effective in protecting epoxy fiberglass composites from atomic oxygen and ultraviolet (UV) degradation. The tape adhesive performed well. The aluminum, however, appeared to have become embrittled by the 5.8 years of space exposure.				
14. SUBJECT TERMS LDEF, Atomic Oxygen, Composites, Thermal Control Tape			15. NUMBER OF PAGES 15	
			16. PRICE CODE NTIS	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT Unlimited	

TABLE OF CONTENTS

	Page
INTRODUCTION	1
LDEF AO171 EXPOSURE CONDITIONS	1
COMPOSITE TEST SPECIMENS	2
VISUAL OBSERVATIONS	2
ALUMINUM THERMAL CONTROL TAPE SEM PHOTOGRAPHS	2
MICROMETEOROID DEBRIS	3
MECHANICAL AND OPTICAL PROPERTIES	3
CONCLUSION	4

LIST OF ILLUSTRATIONS

Figure	Title	Page
1.	Flight experiment AO171, solar array materials passive LDEF experiment (SAMPLE)	5
2.	Tape-covered fiberglass epoxy composite flight and control specimens	6
3.	SEM photograph at $\times 200$ magnification of control tape surface (top) and flight tape surface (bottom)	7
4.	SEM photograph at $\times 1,000$ magnification of control tape surface (top) and flight tape surface (bottom)	8
5.	SEM photograph at $\times 5,000$ magnification of control tape surface (top) and flight tape surface (bottom)	9
6.	SEM photographs at $\times 200$ magnification of debris impacts on flight-exposed tape-covered fiberglass composites	10

LIST OF TABLES

Table	Title	Page
1.	LDEF AO171 exposure conditions	1
2.	Mechanical and optical properties	3

TECHNICAL MEMORANDUM

PERFORMANCE OF THERMAL CONTROL TAPE IN THE PROTECTION OF COMPOSITE MATERIALS TO SPACE ENVIRONMENTAL EXPOSURE

INTRODUCTION

The selection of materials for construction of long duration mission spacecraft has presented many challenges to the aerospace design community. After nearly 6 years in low-Earth orbit, NASA's long duration exposure facility (LDEF), retrieved in January of 1990, has provided valuable information on both the nature of the space environment as well as the effects of the space environment on potential spacecraft materials. Composites, long a favorite of the design community because of a high strength-to-weight ratio, were flown in various configurations on LDEF in order to evaluate the effects of radiation, atomic oxygen, vacuum, micrometeoroid debris, and thermal variations on their performance. Fiberglass composite samples covered with an aluminum thermal control tape were flown as part of flight experiment AO171, the solar array materials passive LDEF experiment (SAMPLE). Visual observations and test results indicate that the thermal control tape suffered little degradation from the space exposure and proved to be a reliable source of protection from the space environment for the underlying composite material.

LDEF AO171 EXPOSURE CONDITIONS

The LDEF AO171 tray was located on the leading edge row 8A of the satellite and was in orbit at an angle of $\sim 38^\circ$ from the ram vector. Table 1 summarizes the environmental exposure conditions for the composite samples. Of particular significance in the evaluation of the thermal control tape performance is the high atomic oxygen fluence level and the large number of thermal cycles.

Table 1. LDEF AO171 exposure conditions.

High Vacuum	10^{-6} to 10^{-7} Torr (estimated)
UV Radiation	10,471 ESH
Proton Fluence	10^9 p+/cm ² (0.5 to 200 MeV)
Electron Fluence	10^{12} to 10^8 e-/cm ² (0.5 to 3.0 MeV)
Atomic Oxygen	6.93×10^{21} atoms/cm ²
Micrometeoroid/Space Debris	2 to 7 impacts per composite, <1 mm
Thermal Cycles	$\sim 32,000$ cycles (temperature TBD)

COMPOSITE TEST SPECIMENS

Six "S" glass epoxy composite samples, 0.5 by 6 inches in size, were flown as part of flight experiment AO171, three of which were covered with an aluminum thermal control tape. Additionally, six composite control samples, three with the thermal control tape, remained in the lab for post-flight comparison. The composite resin was supplied by Air Logistics, and the "S" glass was from Owens Corning S-901 glass. The thermal control tape was a 2-mil aluminum with 2-mil pressure sensitive silicone adhesive SR574. Figure 1 shows the basic flight configuration for the six plates which made up the AO171 tray experiment. The fiberglass epoxy composites, along with the aluminum-covered fiberglass composites, are shown in the post-flight condition in the upper right corner of plate III of figure 1.

VISUAL OBSERVATIONS

In order to evaluate the effects of the space environment on the aluminum thermal control tape, a comparative series of visual and mechanical tests was performed on the tape-covered flight composite samples and the laboratory tape-covered control composite samples. As seen in figure 2, no clear visual distinction can be made between the flight-exposed samples and the control samples. However, because the tape was applied only to the surface of the composites, the edges of the flight samples were exposed to atomic oxygen. The flight sample edges showed clear signs of resin erosion in the composite matrix. A thin oxide layer was also evident on both the exposed and control-tape surfaces. Further work is needed to better quantify the thickness of this oxide layer on the tape.

ALUMINUM THERMAL CONTROL TAPE SEM PHOTOGRAPHS

The thermal control tape surface on the flight and control composite samples was examined using a scanning electric microscope (SEM). Figure 3 compares the SEM photograph taken at $\times 200$ magnification for a control sample (top) and for a flight sample (bottom). Both the control and flight sample photographs show what appears to be fabrication "roll marks." The flight sample SEM photograph, however, also shows evidence of a wave-like crest structure projecting from the surface of the tape.

Figure 4 compares the SEM photograph taken at $\times 1,000$ magnification for the same control sample (top) and flight sample (bottom) as contained in the earlier SEM photographs. In this series of photographs, a clear difference in the surface structure of the two tape specimens is easily seen. The wave-like structure of the flight tape is reminiscent of Luder's bands, a fatigue phenomenon, and may be linked to the high number of thermal cycles that the flight samples underwent. Further analyses are required to confirm this phenomenon.

Finally, figure 5 compares the SEM photograph taken at $\times 5,000$ magnification for the control tape sample (top) and for the exposed tape sample (bottom). The contrast in surface texture between the flight tape and control tape is clearly evident.

MICROMETEOROID DEBRIS

Two of the flight tape-covered glass epoxy specimens showed evidence of a single impact with micrometeoroid/space debris, with each impact measuring less than 1 mm in diameter. While the thermal control tape was able to prevent damage to the composite substrate on one flight sample, the impact on the second sample did penetrate through to the composite substrate causing damage to the underlying fibers. Figure 6 is the SEM photographs of the impact area for the nonpenetrating impact (top) and for the penetrating impact (bottom).

MECHANICAL AND OPTICAL PROPERTIES

Deterioration of composite materials by the space environment is of considerable concern to the aerospace designer. Erosion of the composite matrix resin can lead to degradation in material mechanical strength. The thermal control tape proved successful in protecting the underlying composite from atomic oxygen erosion as evident in the mass loss data. The small degree of mass loss on the tape-covered specimens was due to erosion along the specimen edges where the composite was exposed. The silicone adhesive on the tape also proved to withstand the rigors of the environment, even though the flight specimens showed an increase in peel strength over the control by a factor greater than 2 to 1. The increase in peel strength is suggestive of additional curing (embrittlement), probably brought about by thermal extremes on the high temperature side and by penetrating radiation. Breakage of the aluminum during the peel tests on the flight tape specimens also suggested that the flight tape had become embrittled by the space exposure. This tape embrittlement theory is currently under investigation. The solar absorptance and IR emittance on the tape-covered specimens showed little change between the flight and control specimens, with the differences in recorded values considered to be in the noise range of the portable instruments used to measure the properties. Table 2 summarizes the mechanical and optical properties for the "bare" composite (control and flight) and for the aluminum tape-covered composites (control and flight).

Table 2. Mechanical and optical properties.

	Peel Strength (lb/in)	Mass Loss (mg/cm ²)	Solar α (average)	IR ϵ (average)
<u>Bare Composite</u>				
Control	—	—	0.723	0.894
Flight	—	2.40	0.787	0.895
<u>Tape-Covered Composite</u>				
Control	1.9	—	0.140	0.025
Flight	4.6	0.59	0.103	0.020

CONCLUSION

The aluminum thermal control tape proved effective in protecting the underlying fiberglass epoxy composite from the rigors of the low-Earth orbit space exposure. Although SEM photographs revealed morphology changes in the flight exposed-tape surface, due at least in part to thermal cycling effects, the overall tape performance was not compromised. Mass loss data from the flight tape-covered composite samples and "bare" composite samples clearly indicate that the aluminum tape prevented atomic oxygen erosion of the composite matrix resin. The average peel strength for the flight exposed tapes increased by a factor of nearly 2.5 over the average ground-based control tapes. Solar absorptance and IR emittance data on the aluminum tape varied little between flight exposed samples and control samples. However, the tape did not provide complete protection from micrometeoroid/debris. One debris hit did penetrate the protective tape, causing damage to the composite substrate.





Figure 1. Flight experiment AO171, solar array materials passive LDEF experiment (SAMPLE).

ORIGINAL PAGE
BLACK AND WHITE PHOTOGRAPH



Figure 2. Tape-covered fiberglass epoxy composite flight and control specimens.




(Control Tape Surface)




(Flight Tape Surface)

Figure 3. SEM photograph at $\times 200$ magnification of control tape surface and flight tape surface.




(Control Tape Surface)



(Flight Tape Surface)

Figure 4. SEM photograph at $\times 1,000$ magnification of control tape surface and flight tape surface.




(Control Tape Surface)




(Flight Tape Surface)

Figure 5. SEM photograph at $\times 5,000$ magnification of control tape surface and flight tape surface.



(Nonpenetrating Impact)



(Penetrating Impact)

Figure 6. SEM photographs at $\times 200$ magnification of debris impacts on flight-exposed tape-covered fiberglass composites.

APPROVAL

PERFORMANCE OF THERMAL CONTROL TAPE IN THE PROTECTION OF COMPOSITE MATERIALS TO SPACE ENVIRONMENTAL EXPOSURE

By R.R. Kamenetzky and A.F. Whitaker

The information in this report has been reviewed for technical content. Review of any information concerning Department of Defense or nuclear energy activities or programs has been made by the MSFC Security Classification Officer. This report, in its entirety, has been determined to be unclassified.



P.H. SCHUERER
Director, Materials and Processes Laboratory

